

PRODUCT DATA SHEET

WINDOWSKIN™ PAW55



WINDOWSKIN™ PAW55 is manufactured under strict quality control as a transparent protective film for window glass and most non-porous frames. It is formulated as a surface protection and time saving “tool” to reduce damage caused by allied building trades, and to reduce the cleaning process.

Colour	White (when liquid) Translucent (when dry)
Viscosity	Heavy bodied
Solids by Weight	49%
pH	6.5
Specific Gravity	1.072 Kgs/litre
Number of coats	1 or 2 depending on service requirement
Recommended Surfaces	Clean glass, powdercoated aluminium and polished anodised aluminium are common for easy removal. Other surfaces must be tested thoroughly.
Clean Up:	Clean water

Film Build	60um	75um	85um	100um	120um
Drying Time	20 mins at 20°C	30 mins at 20°C	45 mins at 20°C	60 mins at 20°C	90 mins at 20°C
Application Temperature	2 - 35°C	2 - 35°C	2 - 35°C	2 - 35°C	5 - 35°C
Service Temperature (dry)	-4 - 45°C	-4 - 45°C	-4 - 45°C	-4 - 45°C	-4 - 45°C
Removal Temperature Range	7 - 25°C	7 - 25°C	7 - 25°C	0 - 35°C	0 - 35°C
External with high exposure to direct sunlight & rain					
Serviceable Life*	2 - 7 days	3 - 4 mths	4 - 6 mths	6 - 12 mths	12 - 18 mths
Maximum Exposure+	14 days	6 mths	9 mths	15 mths	24 mths
External with low exposure to direct sunlight & rain					
Serviceable Life*	14-28 days	3 - 6 mths	6 - 9 mths	9 - 15 mths	18 - 24 mths
Maximum Exposure+	1 month	9 mths	12 mths	18 mths	24+ mths
Internal with high exposure to direct sunlight					
Serviceable Life*	1 - 2 mths	6 - 9 mths	9 - 15 mths	18 - 24 mths	24+ mths
Maximum Exposure+	3 mths	12 mths	18 mths	24+ mths	24+ mths
Internal with low exposure to direct sunlight					
Serviceable Life*	6 - 9 mths	9 - 15 mths	18 - 24 mths	24+ mths	24+ mths
Maximum Exposure+	12 mths	18 mths	24+ mths	24+ mths	24+ mths
Removal Aid	Apply water to membrane either with sponge or hose or by mist spray to aid release of product				

* Serviceable Life is defined as the period of recommended exposure whereby good peel-ability of Product is maintained. The Serviceable Life is dependant on the weather conditions the Product is exposed to, with optimal weather conditions being low varying temperatures and climate.

+ Maximum Exposure is defined as the maximum period window skin PAW55 should remain on a surface, however as the Product can neither bake-on or fall-off and can always be removed without any risk of damaging the surface it is protecting the maximum exposure is given as a recommendation only.

This product should only be used in accordance with instructions on this Data Sheet, the container label, or written instructions from the company. This is not a complete specification and all information is given in good faith. Customers should conduct all their own testing to satisfy their requirements. The Franchisor warrants that the Product has been manufactured under strict control to its normal standards. The performance of the Product will vary according to the nature of the surface to which it is applied, the preparation and the mode of application, and the climate it is exposed to. If there is any doubt as to the suitability of the Product consult with the Franchisor.