



Protect-A-Window

AUSTRALIA Pty Ltd

ACN 095 789 138

ABN 67 095 789 138

10/14 Rothcote Crt (PO Box 3255)
Burleigh Town QLD 4220 Australia

Phone: 07 5522 1366

Fax: 07 5522 1799

www.pawindustries.com.au

info@pawindustries.com.au

Local Call 1300 306 712

To whom it may concern:

Re: PAW55 TEST RESULTS

Please refer to attached.

Regards,

A handwritten signature in black ink, appearing to read 'S Reilly'.

Steve Reilly
General Manager

Specialising in Paint-On Peel-Off Temporary Protective Peelable Coatings and Services since 1992.

WindowSKIN™ PAW55 ○ **BenchSKIN™** ○ **TubSKIN®** ○ **AutoSKIN®** ○ **BoothSKIN™** ○ **MarineSKIN™**

www.pawindustries.com.au

www.protectawindow.com.au

www.autoskin.com.au

Members of Housing Industry of Australia, Master Builders Association, & Australian Window Association

LABORATORY REPORT NO 8899
UV EXPOSURE PERFORMANCE OF
PAW 55

Introduction: Samples designated:

- X - applied to both the rubber and powder coated frame.
- Aa - applied to the Comfort Plus inside face
- Ab - applied to the exterior face of the Comfort Plus Sample
- Ba - applied to the inside face of the Energy Advantage
- Bb - applied to the exterior face of the Energy Advantage

All samples were applied at a dry film thickness of 100 + or – 30 microns and exposed in the QUV Weatherometer using the UVB irradiation for 6 hour cycles followed by 4 hour cycles of 100% humidity at 50⁰ C

Observations: Testing was discontinued after 300 hours

The film was easily released from all substrates and had approximately original integrity. Powder coated surface not covered by film became chalky and lost its gloss, however areas protected by film retained gloss.

Conclusions: 300 hours of exposure to UVB irradiation including the humidity cycle may be taken as roughly equivalent to 5 years exterior weather exposure.

It is concluded that the tested sample, identified as above will not lose integrity nor peel-ability within 5 years of outdoor exposure.

26 September 2001

Protect-A-Window certify that an independent qualified chemist has carried out these tests and that the contents of this letter are a true copy of that report. Details of the testing company are available by request only.